

Material Data Sheet for Gas Pressure Sintered Silicon Nitride

1. Material

FCT Denotation	SN-GP
Material Description	Gas Pressure Sintered Silicon Nitride

2. General Properties

Chemical Composition	Si ₃ N ₄ (wt.-%)	85 - 92
	RE ₂ O ₃ /Al ₂ O ₃ (wt.-%)	8 - 15
Bulk Density	ρ [1] (g/cm ³)	3.18 - 3.30
Residual Porosity	(%)	< 1
Open Porosity	(%)	0
Grain Size (Longitudinal Direction)	(μ m)	1 - 15

3. Mechanical Properties

Hardness	[2]	(GPa)	14.5
Compressive Strength		(MPa)	3000
Bendig Strength	σ [3]	(MPa)	670
Weibull-Modulus	m		20
Fracture Toughness	K_{Ic} [4]	(MPam ^{1/2})	6.2
Youngs Modulus	E	(GPa)	290
Poisson Ratio	v		0.26

4. Thermal Properties

Max. Working Temperature			
- Inert Atmosphere		(°C)	1400
- Air		(°C)	1200
Specific Heat Capacity		(J/kgK)	620
Thermal Conductivity	λ (20°C)	(W/mK)	24
Coeff. of Thermal Expansion	α RT-1000°C	(10 ⁻⁶ K ⁻¹)	3.2
Coeff. of Thermal Expansion	α RT \pm 20°C	(10 ⁻⁶ K ⁻¹)	1.4
Thermal Shock Parameter	R₁ [5]	(K)	534
Thermal Shock Parameter	R₂ [6]	(W/m)	12822

5. Specific Properties

Electrical Resistance (20 °C)	(Ω cm)	10 ¹⁴
-------------------------------	----------------	------------------

[1] Determination of density and porosity according to DIN 623-2

[2] Average value of 4-point bending strength at room temperature according to DIN EN 843-1

[3] Hardness according to DIN EN 843-4

[4] Calculated from crack length derived from Vickers hardness indentation, according to Niihara $R_1 = \frac{\sigma(1-\nu)}{E\alpha}$

[5] Critical temperature difference for an infinite high heat transfer (quenching)

[6] Thermal shock coefficient at finite constant heat transfer (slowly heating) $R_2 = \frac{\sigma(1-\nu)}{E\alpha} \lambda$

The material characteristics listed above are measured at testing samples. They cannot be transferred to components with different size, shape or surface properties. We reserve the right to alter properties within the scope of technical progress or new developments.